

**N70/38 Performance Laminated Glass 1/4" (6mm)/ 0.060 PVB / 1/4" (6mm)**

Solar Control Low-E Glass	Visible			Solar		U-Values		Shading Coefficient (SC)	Solar Heat Gain Coefficient (SHGC)	Light to Solar Gain (LSG)
	Trans. %	Refle. Ext %	Refl. Int %	Trans. %	Refle. Ext %	Winter	Summer			
 N70/38 (2) Clear + Clear	72	9	10	33	28	0.95	0.86	0.52	0.45	1.6
 N70/38 (2) Low Iron + Clear	74	9	10	35	40	0.95	0.86	0.49	0.43	1.72
 N70/38 (2) Atlantica + Clear	55	8	7	20	7	0.95	0.86	0.51	0.44	1.25
 N70/38 (2) Azuria + Clear	56	7	9	20	6	0.95	0.86	0.51	0.45	1.24
 N70/38 (2) Pacifica + Clear	35	6	8	15	6	0.95	0.86	0.47	0.41	0.85
 N70/38 (2) Solarblue + Clear	46	6	8	21	12	0.95	0.86	0.49	0.43	1.07
 N70/38 (2) Bronze + Clear	43	6	8	20	15	0.95	0.86	0.48	0.41	1.05
 N70/38 (2) Gray + Clear	36	6	8	17	12	0.95	0.86	0.47	0.41	0.88
 N70/38 (2) Solex + Clear	63	8	9	25	10	0.95	0.86	0.53	0.46	1.37
 N70/38 (2) Vistacool (3) Azuria + Clear	43	14	32	17	10	0.29	0.27	0.28	0.25	1.72
 N70/38 (2) Vistacool (3) Pacifica + Clear	26	9	31	12	8	0.29	0.27	0.23	0.20	1.30
 N70/38 (2) Vistacool (3) Gray + Clear	27	9	31	12	14	0.29	0.27	0.25	0.22	1.23
 N70/38 (3) Atlantica + Clear	53	8	10	20	7	0.29	0.27	0.35	0.31	1.71
 N70/38 (3) Azuria + Clear	54	9	9	21	7	0.32	0.28	0.35	0.31	1.74
 N70/38 (3) Pacifica + Clear	34	6	9	15	7	0.29	0.27	0.29	0.25	1.36
 N70/38 (3) Solarblue + Clear	45	8	8	21	10	0.32	0.28	0.39	0.34	1.32
 N70/38 (3) Bronze + Clear	42	7	9	21	16	0.29	0.27	0.37	0.32	1.31
 N70/38 (3) Gray + Clear	35	7	9	18	13	0.29	0.27	0.23	0.29	1.21
 N70/38 (3) Solex + Clear	61	10	10	25	11	1.65	1.55	0.42	0.37	1.65
 Vistacool (2) Azuria + N70/38 (3) + Clear	38	22	28	14	11	0.22	0.22	0.27	0.23	1.65
 Vistacool (2) Pacifica + N70/38 (3) + Clear	24	11	27	10	9	0.22	0.22	0.22	0.19	1.26
 Vistacool (2) Gray + N70/38 (3) + Clear	25	12	28	13	15	0.22	0.22	0.25	0.22	1.13